

WHAT IS CLAIMED IS:

1. A polarizing film comprising:  
a long polymer film; and  
a dichroic substance,  
wherein the polarizing film has an absorption axis  
in the TD direction of the polarizing film.
2. The polarizing film according to claim 1,  
wherein the length in the MD direction of the  
polarizing film is not smaller than five times as long as  
the length in the TD direction of the polarizing film.
3. The polarizing film according to claim 1,  
wherein the polarizing film is produced by  
stretching the long polymer film in the TD direction.
4. The polarizing film according to claim 1,  
wherein the polarizing film is produced by:  
stretching the long polymer film in the TD  
direction; and  
shrinking the long polymer film in the MD direction.

5. The polarizing film according to claim 1,  
wherein the polarizing film is produced by dyeing  
the long polymer, which is stretched in the TD direction,  
with a iodine by using an aqueous solution containing the  
iodine.

6. The polarizing film according to claim 1,  
wherein the polarizing film is produced by dyeing  
the long polymer, which is stretched in the TD direction  
and shrunk in the MD direction, with a iodine by using an  
aqueous solution containing the iodine.

7. The polarizing film according to claim 5,  
wherein the polarizing film is produced by dyeing  
the long polymer film with the iodine by applying the  
aqueous solution containing the iodine onto the long  
polymer film.

8. A laminated film comprising:  
a polarizing film according to claim 1; and  
a retardation film having a slow axis in the MD  
direction, which comprises a long polymer film,  
wherein the MD direction of the polarizing film  
corresponds to the MD direction of the retardation film.

9. The laminated film according to claim 8,  
wherein the retardation film comprises a uniaxially  
stretched film.

10. The laminated film according to claim 8,  
wherein the retardation film comprises an optically  
uniaxial layer comprising a liquid crystal material.

11. The laminated film according to claim 8,  
wherein the retardation film comprises a  
birefringent layer comprising a non-liquid crystal material  
having a birefringence of not lower than 0.005.

12. The laminated film according to claim 8,  
wherein the retardation film is a composite film  
comprising a birefringent layer provided on a birefringent  
polymer film.

13. The laminated film according to claim 11 or 12,  
wherein the birefringent layer comprises a solid  
polymer containing at least one selected from:  
polyetherketone; polyamide; polyester; polyimide;  
polyamideimide; and polyesterimide.

14. The laminated film according to claim 13,  
wherein the birefringent layer is a solid polymer  
comprising polyimide.

15. The laminated film according to claim 11 or 12,  
wherein the birefringent layer has a relationship  
 $n_x > n_y > n_z$ ,  
wherein  $n_x$  is the maximum in-plane refractive index,  $n_y$  is  
an in-plane refractive index in a direction perpendicular  
to the direction of  $n_x$ , and  $n_z$  is a thicknesswise  
refractive index.

16. A liquid crystal display comprising a polarizing film according to claim 1 that is disposed outside of a liquid crystal cell.

17. A liquid crystal display comprising a laminated film according to claim 8 that is disposed outside of a liquid crystal cell.

18. A process for producing a polarizing film comprising:

unrolling a polymer film successively;  
stretching the polymer film in the TD direction; and  
dyeing the stretched film.

19. The process for producing a polarizing film according to claim 18;

wherein the stretching in the TD direction is carried out by a tenter stretching machine.